## PATENT ABSTRACTS OF JAPAN

(11)Publication number:

09-272987

(43) Date of publication of application: 21.10.1997

(51)Int.CI.

C23C 30/00 C23C 28/00

(21)Application number: 09-022669

\_\_\_\_\_\_\_

(22)Date of filing:

05.02.1997

(71)Applicant : TOSHIBA CORP

(72)Inventor: YASUDA KAZUHIRO

SUENAGA SEIICHI WADA KUNIHIKO

**NAKABASHI MASAKO** 

(30)Priority

Priority number: 08 18565

Priority date: 05.02.1996

Priority country: JP

## (54) HEAT RESISTANT MEMBER

## (57)Abstract:

PROBLEM TO BE SOLVED: To provide a heat resistant member durable against a long term use under a high temp. atmosphere and an operation environment where thermal cycle or thermal shock is impressed by improving both properties of thermal fatigue property and thermal shock resistance of a ceramic heat insulating layer.

SOLUTION: The heat resistant member is provided with the ceramic heat insulating layer 3 formed by applying directly on a metallic base material 1 or through a metallic bonding layer 2 formed on the metallic base material 1. The ceramic heat insulating layer 3 is provided on the metallic bonding layer 2 (or the metallic base material 1) and has a 1st ceramic layer 3a having high elastic modulus and high hardness and a 2nd ceramic layer 3b provided on the 1st ceramic layer 3a and having low elastic modulus and low hardness. The 1st ceramic layer 3a is, for example, a high density layer having ≥88% relative density and the 2nd ceramic layer 3b is a low density layer having <88% relative density.

